

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	13	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	750	MPa	ISO 527
Yield stress	17	MPa	ISO 527
Charpy impact strength, +23°C	80	kJ/m ²	ISO 179/1eU
Ball indentation hardness	33	MPa	ISO 2039-1
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	75	°C	ISO 75-1/-2
Vicat softening temperature, B	50	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Features

Copolymer

Delivery form

Pellets

Applications

Automotive

Special Characteristics

High impact or impact modified

Regional Availability

Europe