

Hifax TKS 428P C12477

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1100	MPa	ISO 527
Flexural modulus, 23°C	1170	MPa	ISO 178
Charpy notched impact strength, +23°C	50	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	7	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	80	°C	ISO 75-1/-2
Vicat softening temperature, A	127	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Features

Copolymer

Applications

Automotive

Regional Availability

Europe