

## Hipolen P EH 7

PP

Hipol a.d.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	0.7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	34	MPa	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178
Izod notched impact strength, +23°C	5.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	52	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, A	150	°C	ISO 306
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion

#### Delivery form

Pellets

#### Features

Melt Strength, Thermal Stability, Homopolymer

#### Chemical Resistance

General Chemical Resistance, Solvent Resistance

#### Regional Availability

Europe