

# Hipolen P MA 71

PP

Hipol a.d.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1400	MPa	ISO 527
Yield stress	34	MPa	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178
Izod notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Regional Availability

Europe

### Features

Homopolymer