

Hostacom EBS 777D White

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	30	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ISO 1183
Moisture Content	0.02	%	-

Characteristics**Processing**

Wire/Cable Extrusion, Casting

Chemical Resistance

General Chemical Resistance

Features

Copolymer

Regional Availability

North America