

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1200	MPa	ISO 178
Izod notched impact strength, +23°C	30	kJ/m ²	ISO 180/1A
Izod notched impact strength	4	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	95	°C	ISO 75-1/-2
Other properties			
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Special Characteristics

High impact or impact modified

Features

Copolymer

Chemical Resistance

Environmental Stress Crack Resistance

Applications

Automotive

Regional Availability

Europe