

Hostalen PP H2150-RC

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	36	MPa	ISO 527
Yield strain	10	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, +23°C	61	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	153	°C	ISO 11357-1/-3
Other properties			
ISO Data			
Density	910	kg/m ³	ISO 1183

Characteristics**Processing**

Pipe/Tube Extrusion, Sheet Extrusion, Other Extrusion

Delivery form

Natural Color

Features

Nucleated, Homopolymer

Chemical Resistance

Oxidation Resistance

Certifications

Food contact, Food approval 1935/2004/EC, Food approval 10/2011

Regional Availability

Europe