

Product Texts

Applications:

Adhesive tapes, BOPP film by the plan process (stenter) or balloon (double bubble), BOPP film with high retention property of the surface treatment, Food packaging, Labels, Metalized film, Pearled opaque films.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.1	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	33	MPa	ASTM D 638
Elongation at Yield	9	%	ASTM D 638
Rockwell Hardness	R 95	-	ASTM D 785
Izod Impact notched, 1/8 in	30	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Characteristics

Features

Good Adhesion, Homopolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

North America, Europe, South and Central America