

HP552R

PP

Persian Gulf Polymer Pooya Tejarat Novin Co.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	32	MPa	ASTM D 638
Elongation at Yield	13	%	ASTM D 638
Flexural Modulus	1500	MPa	ASTM D 790
Rockwell Hardness	R 100	-	ASTM D 785
Izod Impact notched, 1/8 in	30	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	94	°C	ASTM D 648
Vicat Temperature	152	°C	ASTM D 1525
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Fiber Extrusion

Features

Gas Fading Resistance, Homopolymer

Certifications

Food contact

Applications

Medical, Sports Equipment

Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa