

POLYAXIS PD 2000

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.9	MPa	ASTM D 638
Elongation at Break	30	%	ASTM D 638
Flexural Modulus	1289	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	120	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Rotational Molding

Regional Availability

North America