

Polypropylene PP 1467-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	21	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1069	MPa	ASTM D 790
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	90	°C	ASTM D 648
DTUL @ 264 psi	50	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	902	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

Natural Color

Regional Availability

North America