

## Polypropylene PP 1901-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	31.7	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Izod Impact notched, 1/8 in	21.4	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding

#### Features

Homopolymer

#### Applications

Packaging

#### Regional Availability

North America