

Polypropylene PP 2407

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25.5	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1172	MPa	ASTM D 790
Izod Impact notched, 1/8 in	160	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	90	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Regional Availability

North America

Features

Copolymer