

Polypropylene PP 3183

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	26.2	MPa	ASTM D 638
Elongation at Yield	200	%	ASTM D 638
Flexural Modulus	1241	MPa	ASTM D 790
Rockwell Hardness	R75	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	87.8	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion, Blow Molding

Regional Availability

North America