

Polypropylene PP 3409-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	3920	MPa	ASTM D 638
Elongation at Break	26	%	ASTM D 638
Flexural Modulus	1850	MPa	ASTM D 790
Izod Impact notched, 1/8 in	13.5	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	221	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	890	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion

Regional Availability

North America

Features

Copolymer