

Polypropylene PP 3475-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	31.7	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Izod Impact notched, 1/8 in	21.4	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Features

Homopolymer

Delivery form

Natural Color

Regional Availability

North America