

Polypropylene PP 3479-01

PP

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	31	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1310	MPa	ASTM D 790
Rockwell Hardness	R85	-	ASTM D 785
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	87.2	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Blow Molding

Regional Availability

North America

Features

Copolymer, Random Copolymer