

**Polypropylene PP 3482-01**

PP

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>39.3</b>	MPa	ASTM D 638
Elongation at Yield	<b>10</b>	%	ASTM D 638
Flexural Modulus	<b>1931</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R100</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>26.7</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>120</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America

**Features**

Nucleated, Homopolymer