

**Product Texts**

SABIC® PP 520P is particularly designed for extrusion of cast film, both mono layer films and co extruded films. It provides an excellent combination of transparency, stiffness and high heat resistance. SABIC® PP 522L is the anti block and slip agent containing version of SABIC® PP 520P. Application: SABIC® PP 520P is typically used for food packaging, lamination film, stationary film, textile packaging, flower packaging, and hygiene packaging. It offers excellent properties for twist film application. Health, Safety and Food Contact regulations: SABIC® PP 520P has a Food Contact Declaration. SABIC Material Safety Data Sheets (MSDS) and Product Safety Declarations are available on our Internet site <http://www.sabic.com>. The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications. This grade material is UL registered under File E111275 ([www.ul.com](http://www.ul.com))IMDS 7172624

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>1700</b>	MPa	ISO 527
Yield stress	<b>36</b>	MPa	ISO 527
Yield strain	<b>9</b>	%	ISO 527

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Vicat softening temperature, A	<b>154</b>	°C	ISO 306
Vicat softening temperature, B	<b>95</b>	°C	ISO 306

**Characteristics****Certifications**

Food contact