

Product Texts

SABIC® PP 575P is specially developed for producing rigid injection molding articles for general purpose applications. It gives consistent processability and high gloss in the products.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield strain	11	%	ISO 527
ASTM Data			
Tensile Strength at Yield	35	MPa	ASTM D 638
Rockwell Hardness	R104	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	98	°C	ASTM D 648

Characteristics**Processing**

Injection Molding