

**Product Texts**

SABIC® PPcompound 57F9722 is an esthetic UV stabilized automotive exterior grade. This talcum filled copolymer combines good scratch resistance with high stiffness and good thermal dimensional stability. SABIC® PPcompound 57F9722 is a designated automotive grade. IMDS ID: 16487554

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2150	MPa	ISO 527
Yield stress	28	MPa	ISO 527
Stress at break	22	MPa	ISO 527
Strain at break	45	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Charpy notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength	2.3	kJ/m <sup>2</sup>	ISO 180/1A
Shore D hardness	70	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	110	°C	ISO 75-1/-2
Vicat softening temperature, A	140	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1040	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

U.V. stabilized or stable to weather

**Features**

Copolymer