

Product Texts

SABIC® PPcompound 7715 is a mineral filled modified polypropylene. This material combines high scratch resistance with a high stiffness, medium impact and good flow. This material has a broad processing window combined with good esthetical performance. Typical applications include esthetical automotive interior parts such as door panels and interior trim. SABIC® PPcompound 7715 is a designated automotive grade. IMDS ID: 16486651

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1600	MPa	ISO 527
Yield stress	26	MPa	ISO 527
Stress at break	18	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Charpy notched impact strength, +23°C	15	kJ/m ²	ISO 179/1eA
Izod notched impact strength	3	kJ/m ²	ISO 180/1A
Shore D hardness	65	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	115	°C	ISO 75-1/-2
Vicat softening temperature, A	135	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1000	kg/m ³	ISO 1183