

**SABIC® PPcompound 9150**

PP

Saudi Basic Industries Corporation (SABIC)

**Product Texts**

SABIC® PPcompound 9150 is a mineral filled modified polypropylene. This material combines high scratch resistance, high stiffness, good impact and high flow. This material has a property profile that fulfills Ford Interior requirements. Typical applications include esthetical automotive interior parts such as instrument panels, lower and upper dashboard, door panels and trim. SABIC® PPcompound 9150 is a designated automotive grade. IMDS ID: 88530289

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>12</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>1800</b>	MPa	ISO 527
Yield stress	<b>22</b>	MPa	ISO 527
Stress at break	<b>18</b>	MPa	ISO 527
Strain at break	<b>30</b>	%	ISO 527
Flexural modulus, 23°C	<b>2000</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>18</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength	<b>5</b>	kJ/m <sup>2</sup>	ISO 180/1A
Shore D hardness	<b>65</b>	-	ISO 7619-1

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>120</b>	°C	ISO 75-1/-2
Vicat softening temperature, A	<b>130</b>	°C	ISO 306

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1000</b>	kg/m <sup>3</sup>	ISO 1183