

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|-------|-------------------|---------------|
| ISO Data | | | |
| Melt flow index, MFI | 6.3 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Yield stress | 34 | MPa | ISO 527 |
| Yield strain | 10 | % | ISO 527 |
| Flexural modulus, 23°C | 1300 | MPa | ISO 178 |
| Izod notched impact strength, +23°C | 2.5 | kJ/m ² | ISO 180/1A |
| Thermal properties | | | |
| ISO Data | | | |
| Temp. of deflection under load, 1.80 MPa | 60 | °C | ISO 75-1/-2 |
| Vicat softening temperature, A | 155 | °C | ISO 306 |

Characteristics

Processing

Other Extrusion

Regional Availability

Europe, Asia Pacific

Features

Homopolymer