

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	33	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Flexural Modulus	1300	MPa	ASTM D 790
Izod Impact notched, 1/8 in	33	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	101	°C	ASTM D 648
Vicat Temperature	160	°C	ASTM D 1525

Characteristics

Features

Color Stability, Gas Fading Resistance, Homopolymer

Certifications

Food contact

Applications

Multifilament

Regional Availability

Europe, Asia Pacific