

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	0.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	2.1	%	ISO 294-4, 2577
Molding shrinkage, normal	1.9	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1450	MPa	ISO 527
Tensile Strength	25	MPa	ISO 527
Flexural modulus, 23°C	1300	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	90	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	70	°C	ISO 75-1/-2
Vicat softening temperature, B	150	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Electrical properties			
ISO Data			
Electric strength	24	kV/mm	IEC 60243-1
Comparative tracking index	450	-	IEC 60112
Other properties			
Density	915	kg/m ³	ISO 1183

Characteristics

Processing

Other Extrusion

Features

Copolymer

Delivery form

Natural Color

Regional Availability

Europe

Special Characteristics

Flame retardant