

**Stretchene RP1903**

PP

LyondellBasell Industries

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>15</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Melt flow index, MFI	<b>10.5</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>1100</b>	MPa	ISO 527
Yield stress	<b>30</b>	MPa	ISO 527
Yield strain	<b>14</b>	%	ISO 527
Strain at break	<b>&gt;50</b>	%	ISO 527
Charpy impact strength, +23°C	<b>200</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	<b>58</b>	MPa	ISO 2039-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>72</b>	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	<b>905</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding, Blow Molding

**Special Characteristics**

High impact or impact modified, Transparent

**Features**

Nucleated, Copolymer, Random Copolymer

**Chemical Resistance**

General Chemical Resistance

**Certifications**

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

**Applications**

Packaging

**Regional Availability**

Europe, Near East/Africa