

**TAIRIPRO® F4008**

PP

Formosa Chemicals &amp; Fibre Corp.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>7.5</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Mold Shrinkage, MD	<b>0.0175</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>25.5</b>	MPa	ASTM D 638
Elongation at Break	<b>200</b>	%	ASTM D 638
Flexural Modulus	<b>834</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 85</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>63.8</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>85</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Extrusion</b>			
Mold temperature	<b>220 - 240</b>	°C	-

**Characteristics****Processing**

Film Extrusion

**Special Characteristics**

Transparent

**Features**

Tribologic Grade, Copolymer, Random Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR, RoHS compliant

**Regional Availability**

Asia Pacific