

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	27	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	26.5	MPa	ASTM D 638
Elongation at Break	200	%	ASTM D 638
Flexural Modulus	1373	MPa	ASTM D 790
Rockwell Hardness	R 93	-	ASTM D 785
Izod Impact notched, 1/8 in	78.5	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	44.1	J/m	ASTM D 256
Temperature	-20	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	120	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Injection pressure	3 - 6	MPa	-

## Characteristics

### Processing

Injection Molding

### Special Characteristics

High impact or impact modified

### Features

Copolymer, Impact Copolymer

### Certifications

Food contact, Food approval FDA 21 CFR, RoHS compliant

### Regional Availability

Asia Pacific