

Product Texts

Homopolymer for spun bond.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1550	MPa	ISO 527
Yield stress	33	MPa	ISO 527
Yield strain	10	%	ISO 527
Flexural modulus, 23°C	1450	MPa	ISO 178
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A
Rockwell hardness	R 101	-	ISO 2039-2

Thermal properties

	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 0.45 MPa	78	°C	ISO 75-1/-2

Characteristics**Processing**

Injection Molding, Coating

Delivery form

Pellets

Features

Color Stability, Gas Fading Resistance, Low Smoke, Soft Feel, Thermal Stability, Homopolymer

Certifications

Food contact, Food approval BfR, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Applications

General Purpose, Medical, Packaging

Regional Availability

Europe