

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>1750</b>	MPa	ISO 527
Stress at break	<b>20</b>	MPa	ISO 527
Izod notched impact strength, +23°C	<b>10</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength Temperature	<b>4</b> <b>-30</b>	kJ/m <sup>2</sup> °C	ISO 180/1A -

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>163</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>60</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	<b>V-0</b> <b>1.6</b>	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	<b>V-2</b> <b>0.8</b>	class mm	IEC 60695-11-10 -

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>1E13</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>1E15</b>	Ohm	IEC 62631-3-2
Comparative tracking index	<b>600</b>	-	IEC 60112

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1050</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>200 - 240</b>	°C	-
Mold temperature	<b>20 - 50</b>	°C	-
Feed temperature	<b>≤60</b>	°C	-
Holding pressure	<b>40 - 80</b>	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Regional Availability**

Europe