

Product Texts

Process Stability: 3568 features excellent processability and the good physical properties necessary for fibers and multifilaments.

Recommended Applications: 3568 is recommended for staple fibers and bulk continuous filament (BCF) yarns.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	166	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	905	kg/m ³	ASTM D 792

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	204 - 260	°C	-

Characteristics**Processing**

Other Extrusion

Features

Gas Fading Resistance, Homopolymer

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America