

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	3.6	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	39	MPa	ASTM D 638
Elongation at Yield	11.2	%	ASTM D 638
Flexural Modulus	1733	MPa	ASTM D 790
Izod Impact notched, 1/8 in	28.5	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	103	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Features

Homopolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

South and Central America