

WE150CF

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	1000	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	145	°C	ISO 11357-1/-3

Characteristics**Processing**

Film Extrusion

Certifications

Food contact, Medical Grade, Device Master File

Additives

Antiblocking agent

Applications

Medical, Packaging

Special Characteristics

Sterilizable, Steam sterilization

Regional Availability

Europe