

**WG320C**

PP

Borealis A/S

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>18</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>160</b>	°C	ISO 11357-1/-3
Vicat softening temperature, A	<b>147</b>	°C	ISO 306

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>910</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Coating

**Certifications**

Food contact

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Europe

**Chemical Resistance**

Grease Resistance