

**YUHWA POLYPRO 8088**

PP

Korea Petrochemical Ind. Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	7.5	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.015	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	29.4	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Flexural Modulus	942	MPa	ASTM D 790
Rockwell Hardness	R 85	-	ASTM D 785
Izod Impact notched, 1/8 in	49	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melting Temperature	136	°C	ASTM D 3418
Vicat Temperature	120	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

High impact or impact modified

**Applications**

Packaging

**Features**

Heat Sealable, Copolymer, Random Copolymer

**Regional Availability**

Asia Pacific

**Certifications**

Food contact, Food approval FDA 21 CFR