

YUHWA POLYPRO CF3230 C

PP

Korea Petrochemical Ind. Co., Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	7.5	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	29.4	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Flexural Modulus	1030	MPa	ASTM D 790
Rockwell Hardness	R 81	-	ASTM D 785
Izod Impact notched, 1/8 in	49	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	136	°C	ASTM D 3418
Vicat Temperature	125	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Transparent

Applications

Packaging

Features

Copolymer, Random Copolymer

Regional Availability

Asia Pacific