

**3M™ Dyneon™ TFM™ 2033 Z PTFE**

PTFE

Dyneon

Other properties	Value	Unit	Test Standard
Density	<b>2160</b>	kg/m <sup>3</sup>	ISO 1183

Film Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at break, parallel	<b>37</b>	MPa	ISO 527-3
Maximum strain, parallel	<b>430</b>	%	ISO 527-3

**Characteristics****Processing**

Other Extrusion

**Delivery form**

Powder

**Special Characteristics**

Transparent

**Features**

Heat Sealable

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa