

3M™ Dyneon™ TFM™ 2070 Z PTFE

PTFE

Dyneon

Other properties	Value	Unit	Test Standard
Density	2160	kg/m ³	ISO 1183

Film Properties	Value	Unit	Test Standard
ISO Data			
Stress at break, parallel	36	MPa	ISO 527-3
Maximum strain, parallel	400	%	ISO 527-3

Characteristics**Processing**

Other Extrusion

Delivery form

Powder

Special Characteristics

Transparent

Features

Heat Sealable

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa