

# Algoflon® F 6

PTFE

Syensqo

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Dielectric Strength, Short Time	65	kV/mm	ASTM D 149
<b>Other properties</b>			
Density	2170	kg/m <sup>3</sup>	ASTM D 792
Bulk Density	380	kg/m <sup>3</sup>	-

## Characteristics

### Processing

Compression Molding

### Delivery form

Pellets, Powder, White

### Features

Homopolymer

### Chemical Resistance

General Chemical Resistance

### Certifications

Food contact, Food approval FDA 21 CFR

### Regional Availability

North America, Europe, Asia Pacific