

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>[S]</sup></b>			
Tensile Strength	<b>32</b>	MPa	ASTM D 4895
Elongation at Break	<b>350</b>	%	ASTM D 4895

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Bulk Density	<b>475</b>	kg/m <sup>3</sup>	-
<b>Other Standards<sup>[S]</sup></b>			
Density	<b>2150</b>	kg/m <sup>3</sup>	ASTM D 4895

S: These properties are reported by the producer according standards that are different to our defaults.

**Characteristics**

**Processing**

Pipe/Tube Extrusion

**Delivery form**

Powder, White

**Special Characteristics**

Transparent

**Features**

Tribologic Grade, Weldable

**Chemical Resistance**

General Chemical Resistance, Environmental Stress Crack Resistance, Solvent Resistance

**Regional Availability**

North America, Europe, Asia Pacific