

124C

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	22.1	MPa	ASTM D 638
Shore D Hardness	65	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	3.05	mm	-
Limiting Oxygen Index	30	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1460	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America