

16903

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	18.6	MPa	ASTM D 638
Shore A Hardness	92	-	ASTM D 2240
Thermal properties			
ASTM Data			
Limiting Oxygen Index	29	%	ASTM D 2863
Other properties			
Density	1380	kg/m ³	ASTM D 792

Characteristics**Processing**

Wire/Cable Extrusion

Regional Availability

North America

Special Characteristics

Flame retardant, Light stabilized or stable to light