

18731

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	16.5	MPa	ASTM D 638
Shore A Hardness	73	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	25	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1340	kg/m ³	ASTM D 792

Characteristics**Processing**

Wire/Cable Extrusion

Regional Availability

North America

Special Characteristics

Light stabilized or stable to light