

19465

PVC, Flexible

Westlake Chemical Corp.

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Strength | 24.1 | MPa | ASTM D 638 |
| Shore D Hardness | 46 | - | ASTM D 2240 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Limiting Oxygen Index | 30.5 | % | ASTM D 2863 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1320 | kg/m ³ | ASTM D 792 |

Characteristics**Processing**

Wire/Cable Extrusion

Chemical Resistance

Oil Resistance

Special Characteristics

Light stabilized or stable to light

Regional Availability

North America