

19901

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	16.9	MPa	ASTM D 638
Shore A Hardness	90	-	ASTM D 2240
Thermal properties			
ASTM Data			
Limiting Oxygen Index	28	%	ASTM D 2863
Electrical properties			
ASTM Data			
Volume Resistivity	1.5E15	Ohm*cm	ASTM D 257
Other properties			
Density	1320	kg/m ³	ASTM D 792

Characteristics**Regional Availability**

North America