

22851

PVC, Flexible

Westlake Chemical Corp.

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------------|----------------------|
| ASTM Data | | | |
| Tensile Strength | 19.7 | MPa | ASTM D 638 |
| Shore A Hardness | 85 | - | ASTM D 2240 |
| Thermal properties | | | |
| ASTM Data | | | |
| Limiting Oxygen Index | 30.5 | % | ASTM D 2863 |
| Other properties | | | |
| Density | 1350 | kg/m ³ | ASTM D 792 |

Characteristics

Special Characteristics

Flame retardant, Light stabilized or stable to light

Regional Availability

North America

Applications

Electrical and Electronical