

28850

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	16.5	MPa	ASTM D 638
Shore A Hardness	85	-	ASTM D 2240
Thermal properties			
ASTM Data			
Limiting Oxygen Index	29.5	%	ASTM D 2863
Other properties			
Density	1360	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

U.V. stabilized or stable to weather

Features

Soft Feel

Chemical Resistance

Oil Resistance

Applications

Electrical and Electronical

Regional Availability

North America