

28930

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	20.7	MPa	ASTM D 638
Shore A Hardness	93	-	ASTM D 2240
Thermal properties			
ASTM Data			
Limiting Oxygen Index	33.5	%	ASTM D 2863
Other properties			
Density	1410	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America

Applications

Electrical and Electronical