

59770

PVC, Flexible

Westlake Chemical Corp.

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	14.5	MPa	ASTM D 638
Shore A Hardness	77	-	ASTM D 2240
Thermal properties			
ASTM Data			
Limiting Oxygen Index	24	%	ASTM D 2863
Other properties			
Density	1260	kg/m ³	ASTM D 792

Characteristics

Processing

Wire/Cable Extrusion

Regional Availability

North America

Special Characteristics

Light stabilized or stable to light